



Technical Data Sheet

DOWSIL™ 795 Structural Glazing Sealant

One-part, neutral-cure silicone sealant

Features & Benefits

- Meets ASTM C1184 for Structural Silicone Sealant
- Meets ASTM C719 Class 50 High movement capability $\pm 50\%$ in well designed weatherseal joint
- Excellent adhesion to a wide range of substrates including glass, anodized and coated aluminum profiles
- Non corrosive cure system
- Ease of use – all-temperature gunnability and easy tooling
- The cured product exhibits excellent weathering characteristics, and a high resistance to ultra-violet radiation, heat and humidity
- High ultimate tensile strength which makes it suitable for structural bonding applications
- Excellent mechanical properties

Composition

- One-part, neutral-cure, RTV silicone sealant

Applications

- DOWSIL™ 795 Structural Glazing Sealant is a one-component Silicone sealant designed for site or factory glazing and curtainwall production. It requires contact with air as it reacts with atmospheric moisture to cure to a tough but flexible silicone rubber. DOWSIL 795 Structural Glazing Sealant can be used where dual structural and weatherseal applications are desired. It has up to $\pm 50\%$ movement capability in a well-designed weatherseal joint.

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Test ¹	Property	Unit	Result
As supplied			
ASTM C 679	Tack-free time, 50% RH	Hours	1.5 (max)
	Curing time at 25°C, 50% RH	Days	7-14
	Full adhesion	Days	14-21
ASTM C 639	Flow, sag or slump	mm	0
	Working time	Minutes	20-30
	Specific gravity		

1. ASTM – American Society for Testing and Materials.

Typical Properties (Cont.)

Test	Property	Unit	Result
	VOC content ²	g/l	32
As cured - 7 days at 25°C (77°F), 50% RH			
ASTM D 412	Tensile strength (ultimate)	MPa	2.3
	Elongation	%	670
ASTM C 661	Durometer hardness, Shore A	Points	35
ASTM D 624	Tear strength, die B	kN/m	13
As cured – after 21 days at 25°C (77°F), 50% RH			
ASTM C 794	Peel strength	kg/cm	8.5
ASTM C 1135	Tensile strength, at 100% elongation	MPa	0.6
	Ultimate tensile strength, at break	MPa	1.2
	Ultimate elongation at break	%	400
ASTM C 719	Joint movement capability	%	±50
As cured – after 21 days at 25°C, 50% relative humidity followed by 5,000 hours in a quv weatherometer, ASTM G 154-06			
ASTM C 1135	Tensile strength, at 100% elongation	MPa	0.6
	Ultimate tensile strength, at break	MPa	1.1

2. Based on South Coast Air Quality Management District of California. Maximum VOC is listed both inclusive and exclusive of water and exempt compounds. For a VOC data sheet for a specific sealant color, please send your request to Dow .

Description

DOWSIL 795 Structural Glazing Sealant is a one-part, neutral-cure, architectural-grade sealant that easily extrudes over a wide temperature range. This cold-applied, non-sagging silicone material cures to a medium- modulus rubber upon exposure to atmospheric moisture. The cured sealant is durable and flexible enough to accommodate ±50% movement of original joint dimension when installed in a properly designed weatherseal joint. In a properly designed structurally glazed joint, the sealant is strong enough to support glass and other panel materials under high wind-load and seismic effects.

Approvals/ Specifications

DOWSIL 795 Structural Glazing Sealant meets the requirements of: ASTM Specification C 1184 for structural silicone sealants ASTM Specification C 920, Class 50.



SGBP 2017-1247

Colors	DOWSIL 795 Structural Glazing Sealant is available in 4 colors: black, white, gray and bronze.
How To Use	<p>When DOWSIL 795 Structural Glazing Sealant is used in structural applications the structural joint design MUST be reviewed by a technical service specialist.</p> <p>Complete design and installation guidelines are contained in the Asia Technical Manual, and must be followed for warranty applications when using this product.</p>
Joint Design	Structural joints sealed with DOWSIL 795 Structural Glazing Sealant should have a minimum depth (or bite) of 6 mm. For large site- glazed joints the sealant or bite should be not more than 12 mm when the sealant can cure from one side only. When an open-cell moisture-permeable spacer tape is used, a structural bite up to 24 mm can cure to optimum strength. The exact structural bite should always be calculated. The thickness of the structural sealant joint or glueline should be 6 mm minimum. As it must accommodate thermal and dynamic movements the actual joint movements should be calculated. Ideally the bite to glueline ratio should be not more than about 3:1.
Accessory Selection	The appropriate selection of all accessories such as setting blocks and backing materials is important to avoid discoloration or adhesion-related problems due to incompatibility. Dow will also assess the suitability of proposed accessory materials as part of the standard testing services. Silicone-based setting blocks are generally recommended for best compatibility.
Preparatory Work	Thoroughly clean all substrates to be sealed, removing all contaminants such as grease, oil, dust, frost or water. All metal, glass, or other surfaces should be cleaned with the recommended solvent, using a lint free cloth.
Method Of Application	Install backing material or joint filler, setting blocks, spacer shims and tapes. Mask areas adjacent to joints to ensure neat sealant lines. Apply DOWSIL 795 Structural Glazing Sealant in a continuous operation using positive pressure. (The sealant can be applied using many types of air-operated guns and most types of bulk dispensing equipment.) Before a skin forms (typically within 15 minutes), tool the sealant with light pressure to spread the sealant against the backing material and joint surfaces. Remove masking tape as soon as the bead is tooled.
Handling Precautions	PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT CONSUMER.DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.

Usable Life And Storage

When stored at or below 27°C (80°F), DOWSIL 795 Structural Glazing Sealant has a shelf life of 12 months from the date of manufacture. Refer to product packaging for "Use By Date."

When stored at or below 27°C (80°F), DOWSIL 795 Structural Glazing Sealant has a shelf life of 12 months from the date of manufacture. Refer to product packaging for "Use By Date."

Questions about the use of DOWSIL 795 Structural Glazing Sealant can be answered by calling your local application sales engineer. Our laboratory personnel and technical service staff are also available for assistance.

Packaging Information

DOWSIL 795 Structural Glazing Sealant is supplied in 300 ml disposable plastic cartridges and 600 ml foil sausages.

Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

DOWSIL 795 Structural Glazing Sealant should not be used for structural applications without the prior written approval of the Construction Industry Technical Services Department. Each project should be specifically and separately approved by Dow.

Project specific approval involves the following prerequisites:

- Joint dimensioning and print reviews.
- Successful laboratory adhesion and compatibility testing to all building components.
- Observance of professional sealant application and workmanship standards.
- Users should always consult the Technical Services Department for adhesion recommendation.

Dow shall not be held liable for any possible claims arising from structural glazing use of DOWSIL 795 Structural Glazing Sealant for projects which have not been specifically approved by Dow.

For projects which have been approved, Dow will issue a structural adhesion warranty on a case by case basis at the user's request. It is the user's exclusive responsibility to ensure project compliance with local building regulations.

Health And Environmental Information

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, www.consumer.dow.com or consult your local Dow representative.

UNRESTRICTED – May be shared with anyone

®™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

DOWSIL™ 795 Structural Glazing Sealant

© 2018 The Dow Chemical Company. All rights reserved.

<http://www.consumer.dow.com>

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

